

## Silicon carbide powders for solid-state (SSiC) or liquid-phase (LP-SiC) sintered technical ceramics

Fine silicon carbide powders produced to specific surface area and purity for high performance structural ceramic applications. The powders are specially designed to obtain optimum sinterability in production of solid state (SSiC) and liquid phase (LP-SiC) sintering applications.

Packaging 25 kg cardboard or 500 kg big bags.


### Typical chemistry

	Free-SiO <sub>2</sub>	Free-Si	Free-C	Tot. Oxygen	S.S.A.	pH
<b>Sintex 10C</b>	0.60%	0.05%	0.20%	0.65%	10 m <sup>2</sup> /g	6 – 7
<b>Sintex 13</b>	1.50%	0.50%	0.30%	1.75%	13 m <sup>2</sup> /g	7 – 8
<b>Sintex 13C</b>	0.70%	0.05%	0.15%	0.75%	13 m <sup>2</sup> /g	6 – 7
<b>Sintex 15</b>	1.20%	0.10%	0.20%	1.20%	15 m <sup>2</sup> /g	6 – 7
<b>Sintex 15C</b>	0.75%	0.05%	0.20%	0.85%	15 m <sup>2</sup> /g	6 – 7
<b>Sintex 25</b>	na	0.10%	0.50%	1.60%	25 m <sup>2</sup> /g	7 – 8
Analytical procedures:	ANSI 74.15 1992			LECO	Micromeritics Gemini V	25 gr. SiC + 50 ml D.I.H <sub>2</sub> O

### Typical trace elements

	Tot. Fe ppm	Tot. Al ppm	Tot. Ni ppm	Tot. V ppm	Tot. Na ppm	Tot. Cr ppm	Tot. Ca ppm	Tot. Ti ppm	Tot. Mg ppm	Tot. K ppm
<b>Sintex 10C</b>	30	400	< 10	70	< 100	< 10	20	200	< 100	20
<b>Sintex 13</b>	1500	1750	na	na	na	na	na	na	na	na
<b>Sintex 13C</b>	50	1200	< 10	70	< 100	< 10	20	200	< 100	20
<b>Sintex 15</b>	350	400	< 10	70	< 100	< 10	20	200	< 100	20
<b>Sintex 15C</b>	50	250	< 10	70	< 100	< 10	20	200	< 100	20
<b>Sintex 25</b>	450	500	< 10	70	< 100	< 10	20	200	< 100	20
Analytical procedures:	X-RAY Fluorescence									

### Typical SIKA® sedimentation curves (Sedigraph®)



The information contained in this Product Information Document is the sole property of Fiven, and cannot be distributed outside Fiven or its Customers, entirely or by parts, without the prior consent of Fiven. The Product Information Documents display typical characteristics for Fiven's products as currently produced in Fiven's various manufacturing locations. These typical characteristics do not constitute a precise Customer Specification, which has to be elaborated separately between the Customer and Fiven in the frame of a commercial offer. Only with this precise Customer Specification can Fiven be bound to any commitment or liability regarding the quality of its products.