

High-purity silicon carbide powder for semiconductor and electronic applications

High-purity silicon carbide, manufactured using the Acheson process, is utilized in the semiconductor industry for a wide range of components and devices, including wafer boats, paddles, tubes, flanges, and more.

Typical chemistry

Char. description	Unit	Value
PSD instrument		Sedigraph
ds 15%	µm	0,5
ds 50%	µm	2,1
ds 95%	µm	8,3
pH	-	5,0
Surface Area	g/cm ³	6,7
Conductivity	µS/cm	7,8
Free C	%	0,29
Free Si	%	0,11
Total O ₂	%	0,88
Al	ppm	111
Ti	ppm	54
V	ppm	87
Fe	ppm	395
Ni	ppm	45
Ca	ppm	19
Zr	ppm	11

Analytical procedures:

All measurement is in accordance to FEPA, ANSI or JIS, or other methods in agreement with customers.

The information contained in this Product Information document is the sole property of Fiven, and cannot be distributed outside Fiven or its Customers, entirely or in parts, without prior consent of Fiven. The Product Information documents display typical characteristics for Fiven's products as currently produced in Fiven's various manufacturing locations. These typical characteristics do not constitute a precise Customer Specification, which must be developed through commercial discussions between Customers and Fiven. Only with this precise Customer Specification can Fiven assume any commitments or liabilities related to the quality of its product.