

Green silicon carbide grains for abrasive applications

Chemically treated, high purity green silicon carbide in macro and micro grains, produced to comply with FEPA standard and particularly suitable for high quality vitrified or resin bonded grinding wheels, honing stones, lapping and polishing applications.

Packaging 1.000 kg or 25 kg paper bags. 500kg big bags on request.

Typical chemistry

	SiC	Free-C	Free-SiO ₂	Free-Si	Fe ₂ O ₃	MI
SIKA® ABR I macro	99.60%	0.15%	0.15%	0.10%		0.01%
SIKA® ABR I micro	99.60%	0.15%	0.10%	0.10%	0.1%	

Grit sizes and shapes

Macro grits			Micro grits		
Grit no.	Mean-Ø mm	LPD g/cm ³	Grit no.	Mean-Ø mm	LPD g/cm ³
F 24	0.750	1.47 - 1.57	F 230	53.0	1.20 - 1.32
F 30	0.630	1.48 - 1.58	F 240	44.5	1.18 - 1.30
F 36	0.530	1.47 - 1.57	F 280	36.5	1.13 - 1.29
F 40	0.450	1.49 - 1.59	F 320	29.2	1.05 - 1.21
F 46	0.390	1.46 - 1.56	F 360	22.8	1.02 - 1.18
F 54	0.320	1.46 - 1.56	F 400	17.3	0.91 - 1.13
F 60	0.270	1.46 - 1.56	F 500	12.8	0.85 - 1.07
F 70	0.220	1.44 - 1.54	F 600	9.3	0.77 - 0.99
F 80	0.190	1.42 - 1.52	F 800	6.5	0.68 - 0.90
F 90	0.155	1.42 - 1.52	F 1000	4.5	NA
F 100	0.130	1.48 - 1.58	F 1200	3.0	NA
F 120	0.110	1.40 - 1.50	F 1500	2.0	NA
F 150	0.090	1.36 - 1.48	F 2000	1.2	NA
F 180	0.075	1.33 - 1.45			
F 220	0.063	1.28 - 1.40			

Analytical procedures:

Particle Size distribution is measured according to FEPA Standard 42-1 for Macro-, and 42-2 for Micro-grains
 LPD = Loose Pack Density is measured according to FEPA Standard 44-1 for Macro-, and 44-2 for Micro-grains
 Magnetic Iron (MI) measured according ANSI B74.19
 Chemistry according ANSI B74.15

The information contained in this Product Information Document is the sole property of Kymera International, and cannot be distributed outside Kymera International or its Customers, entirely or by parts, without the prior consent of Kymera International. The Product Information Documents display typical characteristics for Kymera International's products as currently produced in Kymera International's various manufacturing locations. These typical characteristics do not constitute a precise Customer Specification, which has to be elaborated separately between the Customer and Kymera International in the frame of a commercial offer. Only with this precise Customer Specification can Kymera International be bound to any commitment or liability regarding the quality of its products.