

Silicon carbide ready-to-press granules for hot-pressing technical ceramics.

Densitec 13H granules are spray dried granules, based on our standard black Sintex 13C for hot-pressing technical ceramics. The premix is doped with sintering additives, a low content of temporary binder and pressing aids, and is ready for direct hot-pressing or uniaxial pre-pressing and hot-pressing.

Packaging 15 kg plastic pails

Composition

	Sintering additives		Binder content (total organic)	Moisture content	SiC type
	Carbon	Boron	%	%	
Densitec 13H	Carbon black	Boron carbide	approx. 2.0	approx. 0.6	Sintex 13C


Typical physical properties of granules

	Size		Bulk density	Hall flowmeter	Appearance
	max	Average	g/cm ³	Sec / 25g	
Densitec 13H	250	100	0.88	60	Dark color

Typical physical properties of sintered material

	Density	Microhardness HV 1000	Indentation fracture toughness, K _{IC}	Linear shrinkage	Bending strength
	g/cm ³	GPa	MPa/m	%	4 point MPa
Densitec 13H	3.19	25	3.5	approx. 18	550

Typical Sintering Cycles



The information contained in this Product Information Document is the sole property of Kymera International, and cannot be distributed outside Kymera International or its Customers, entirely or by parts, without the prior consent of Kymera International. The Product Information Documents display typical characteristics for Kymera International's products as currently produced in Kymera International's various manufacturing locations. These typical characteristics do not constitute a precise Customer Specification, which has to be elaborated separately between the Customer and Kymera International in the frame of a commercial offer. Only with this precise Customer Specification can Kymera International be bound to any commitment or liability regarding the quality of its products.